

Material: SAE AMS 4264

Standard Specification for Bronze, Aluminum Silicon, Rods Bars and Forgings

Group: Non-Ferrous Copper Alloy

Sub Group: SAE AMS Bronze, Aluminum Silicon, Rods Bars and Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar and Forging

Chemical Composition		
Aluminium	Al %	6.300 - 7.600
Arsenic	As %	0.150 max.
Iron	Fe %	0.300 max.
Manganese	Mn %	0.100 max.
Ni + Co	Ni% + Co%	0.250 max.
Lead	Pb %	0.050 max.
Silicon	Si %	1.500 - 2.200
Tin	Sn %	0.200 max.
Zinc	Zn %	0.500 max.
Cu + Ag	Cu% + Ag%	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Drawn or Stress Relieving or Hot Rolled

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	310 min.
Elongation in %	9 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C64200	UNS	USA	Rod, Bar, Tube and Shapes
B124 C64200	ASTM	USA	Rod, Bar and Shape
B283 C64200	ASTM	USA	Forging
SB-150 C64200	ASME	USA	Rod, Bar and Shape
SB-283 C64200	ASME	USA	Forging
4633	SAE	USA	Rod, Bar and Forging
4634	SAE	USA	Rod, Bar and Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India