

Material: SAE Hastelloy C276

Standard Specification for Nickel and Nickel-Related Alloys

Group: Non-Ferrous Nickel Alloys

Sub Group: SAE Hastelloy C276 Nickel and Nickel-Related Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.020 max.
Chromium	Cr %	16.000 max.
Iron	Fe %	6.000 max.
Manganese	Mn %	1.000 max.
Molybdenum	Mo %	16.000 max.
Silicon	Si %	0.050 max.
Tungsten	W %	4.000 max.
Ni + Co	Ni% + Co%	57.000 min.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	759 - 1000
Yield Strength in Mpa	462 - 828
Elongation in %	24 - 60
Reduction of Area in %	-
Hardness in HRC	90 - 105
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N10276	UNS	USA	Casting
UNITEMP C 276	SAE	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India