

Material: SAE Inconel 625

Standard Specification for Nickel Alloy, Corrosion and Heat-Resistant, Sheet, Strip and Plate

Group: Non-Ferrous Nickel Alloys

Sub Group: SAE Inconel 625 Nickel Alloy, Corrosion and Heat-Resistant, Sheet, Strip and Plate

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Sheet, Strip and Plate

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	20.000 - 23.000		
Molybdenum	Mo %	8.000 - 10.000		
Iron	Fe %	5.000 max.		
Aluminium	Al %	0.400 max.		
Niobium	Nb %	3.150 - 4.150		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.015 max.		
			Mechanical Properties	
Cobalt	Co %	0.100 max.	Tensile Strength in Mpa	689 - 1104
Titanium	Ti %	0.400 max.	Yield Strength in Mpa	276 - 759
Nickel	Ni %	Balance	Elongation in %	25 - 65
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	110 - 287
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N06250	UNS	USA	Sheet, Strip and Plate
B622 N06250	ASTM	USA	Pipe and Tube
SB-622 N06250	ASME	USA	Pipe and Tube
F3056 N06625 CLASS A	ASTM	USA	Pipe and Tube
F3056 N06625 CLASS B	ASTM	USA	Pipe and Tube
F3056 N06625 CLASS C	ASTM	USA	Pipe and Tube
SIMALLOY 625	SAE	USA	Pipe and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com