

Material: SAE J403 | J1397 UNS G10160 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets, Tubing

Group: Ferrous Stainless Steel Alloys

Sub Group: SAE J403 | J1397 UNS G10160 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 - 0.180	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	210 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in HB	111 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1016	SAE	USA	Bars, Wire Rods and Tubing
1016	AISI	USA	Tubing
A 1040 1016	ASTM	USA	Steel
A 108 Grade 1016	ASTM	USA	Steel and Bar
A 29 1016	ASTM	USA	Steel and Bar
A 510 1016	ASTM	USA	Wire Rods
A 512 Grade 1016	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com