

Material: SAE J403 | SAE J1397 UNS G10210 - Cold Drawn

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: SAE J403 | SAE J1397 UNS G10210 - Cold Drawn Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 - 0.230	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 470 min. Yield Strength in Mpa 390 min. Elongation in % 15 min. Reduction of Area in % 40 min. Hardness in HB 131 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1021	SAE	USA	Bending and Flaring
1021	AISI	USA	Tubing
A 1040 1021	ASTM	USA	Steel
A 29 1021	ASTM	USA	Steel and Bar
A 510 1021	ASTM	USA	Wire Rod and Round Wire
A 512 Grade 1021	ASTM	USA	Tubing
A 513 Grade 1021	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com