

Material: SAE J403 | SAE J1397 UNS G10300 - Cold Drawn
Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-
Group: Ferrous Mild Steel Alloys
Sub Group: SAE J403 | SAE J1397 UNS G10300 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled An
Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 - 0.340	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 520 min. Yield Strength in Mpa 440 min. Elongation in % 12 min. Reduction of Area in % 35 min. Hardness in BHN 149 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1030.0000	SAE	USA	Steel
1030	AISI	USA	Tubing
A 1040 1030	ASTM	USA	Steel
A 108 Grade 1030	ASTM	USA	Steel and Bar
A 29 1030	ASTM	USA	Steel and Bar
A 510 1030	ASTM	USA	Wire Rod and Round Wire
A 512 Grade 1030	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com