

**Material: SAE J403 | SAE J1397 UNS G10500 - Cold Drawn
Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing**

Group: Ferrous Mild Steel Alloys

Sub Group: SAE J403 / SAE J1397 UNS G10500 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment
Carbon	C %	0.480 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering
Manganese	Mn %	0.600 - 0.900	
Phosphorus	P %	0.030 max.	
Sulphur	S %	0.050 max.	
Iron	Fe %	Balance	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
Mechanical Properties			
			Tensile Strength in Mpa
			690 min.
			Yield Strength in Mpa
			580 min.
			Elongation in %
			10 min.
			Reduction of Area in %
			30 min.
			Hardness in BHN
			197 max.
			Impact in Joule
			-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1050	SAE	USA	Steel, Sheet, Strip and Plate
1050	AISI	USA	Steel, Sheet, Strip and Plate
A 311 1050 Class A	ASTM	USA	Steel and Bar
A 311 1050 Class B	ASTM	USA	Steel and Bar
A 513 Grade 1050	ASTM	USA	Steel and Tubing
A 684 Grade 1050	ASTM	USA	Steel and Strip
A 108 Grade 1050	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com