

**Material: SAE J403 | SAE J1397 UNS G11170 - Cold Drawn  
Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing**

### **Group: Ferrous Mild Steel Alloys**

**Sub Group: SAE J403 / SAE J1397 UNS G11170 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing**

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

## **Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing**

Chemical Composition			Heat Treatment	
Carbon	C %	0.140 - 0.200	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.000 - 1.300		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.080 - 0.130		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
Mechanical Properties				
Tensile Strength in Mpa		480 min.		
Yield Strength in Mpa		400 min.		
Elongation in %		15 min.		
Reduction of Area in %		40 min.		
Hardness in BHN		137 max.		
Impact in Joule		-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1117	SAE	USA	Steel, Bar, Forging and Tubing
1117	AISI	USA	Steel and Bar
SUM 31	JIS	Japan	Steel
A 576 1117	ASTM	USA	Steel and Bar
SA-311 1117 Class A	ASME	USA	Steel and Bar
A 576 11L17	ASTM	USA	Steel and Bar
A 29 1117	ASTM	USA	Steel and Bar

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)