

Material: SAE J462 660

Standard Specification for Cast Copper Alloys

Group: Non-Ferrous Copper Alloy

Sub Group: SAE J462 Cast Copper Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition		
Aluminium	Al %	0.005 max.
Iron	Fe %	0.200 max.
Nickel	Ni %	0.500 max.
Phosphorus	P %	0.150 max.
Lead	Pb %	6.000 - 8.000
Aluminium	Al %	0.350 max.
Silicon	Si %	0.005 max.
Tin	Sn %	6.200 - 7.500
Zinc	Zn %	2.000 - 4.000
Copper	Cu %	81.000 - 85.000
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast	

Mechanical Properties	
Tensile Strength in Mpa	207 - 241
Yield Strength in Mpa	138 min.
Elongation in %	10 - 12
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C93200	UNS	USA	Rod, Bar, Tube and Shapes
B30 C93200	ASTM	USA	Ingot and Casting
SB-505 C93200	ASME	USA	Casting
SB-584 C93200	ASME	USA	Casting
C93200	SAE	USA	Casting
C93200	AS	Australia	Ingot and Casting
CA932	SAE	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com