

Material: SAE J462 C87400

Standard Specification for Cast Copper Alloys

Group: Non-Ferrous Copper Alloy

Sub Group: SAE J462 Cast Copper Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.800 max.	As-Cast	
Lead	Pb %	1.000 max.		
Silicon	Si %	2.500 - 4.000		
Zinc	Zn %	12.000 - 16.000		
Copper	Cu %	79.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	345 min.
-	-	-	Yield Strength in Mpa	145 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C87400	UNS	USA	Rod, Bar, Tube and Shapes
B271 C87400	ASTM	USA	Casting
B30 C87400	ASTM	USA	Ingot and Casting
B584 C87400	ASTM	USA	Casting
SB-584 C87400	ASME	USA	Casting
CA874	SAE	USA	Casting
CACIn803	KS	Korea	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com