

## Material: SFS EN 1706 AC- 51200

### Standard Specification for Aluminium and Aluminium Alloys - Casting

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** SFS EN 1706 Aluminium and Aluminium Alloys - Casting

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Iron	Fe %	1.000 max.		
Magnesium	Mg %	8.000 - 10.500		
Manganese	Mn %	0.550 max.		
Nickel	Ni %	0.100 max.		
Silicon	Si %	2.500 max.		
Titanium	Ti %	0.200 max.		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.100 max.		
Beryllium	Be %	0.005 max.		
Zinc	Zn %	1.500 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		

  

Mechanical Properties	
Tensile Strength in Mpa	160 - 180
Yield Strength in Mpa	100 - 110
Elongation in %	3 min.
Reduction of Area in %	-
Hardness in HB	60 - 65
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-51200	DIN	Germany	Casting
EN AC-51200	BS	British	Casting
EN AC-51200	ASME	USA	Casting
EN AC-51200	AFNOR NF	France	Casting
EN AC-51200	UNE	Spain	Casting
EN AC-51200	UNI	Italy	Casting
Al Mg9	ISO	International	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)