

Material: SFS EN 1706 AC- 71100

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: SFS EN 1706 Aluminium and Aluminium Alloys - Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast or Aging	
Iron	Fe %	0.450 max.		
Magnesium	Mg %	0.200 - 0.500		
Manganese	Mn %	0.450 max.		
Silicon	Si %	7.500 - 9.500		
Titanium	Ti %	0.150 max.		
Zinc	Zn %	9.000 - 10.500		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	210 - 260
			Yield Strength in Mpa	190 - 220
			Elongation in %	1 - 3
			Reduction of Area in %	-
			Hardness in HB	80 - 100
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC- 71100	DIN	Germany	Casting
EN AC- 71100	BS	British	Casting
EN AC- 71100	ASME	USA	Casting
EN AC- 71100	AFNOR NF	France	Casting
EN AC- 71100	UNE	Spain	Casting
EN AC-71100	UNI	Italy	Casting
Al Zn10Si8Mg	ISO	International	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com