

Material: SFS EN 1706 AC-46200

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: SFS EN 1706 Aluminium and Aluminium Alloys - Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	2.000 - 3.500	As-Cast	
Iron	Fe %	0.800 max.		
Magnesium	Mg %	0.050 - 0.550		
Manganese	Mn %	0.150 - 0.650		
Nickel	Ni %	0.350 max.		
Silicon	Si %	7.500 - 9.500		
Lead	Pb %	0.250 max.		
Tin	Sn %	0.150 max.		
Titanium	Ti %	0.250 max.		
Zinc	Zn %	1.200 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

Mechanical Properties	
Tensile Strength in Mpa	150 - 370
Yield Strength in Mpa	90 - 310
Elongation in %	1 - 2
Reduction of Area in %	-
Hardness in HB	60 - 120
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-46200	DIN	Germany	Casting
EN AC-46200	BS	British	Casting
EN AC-46200	ASME	USA	Casting
EN AC-46200	UNI	Italy	Casting
EN AC-46200	UNE	Spain	Casting
Al Si8Cu3	ISO	International	Casting
EN AC-46200	AFNOR NF	France	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com