

# Material: SFS EN 1982 CC490K

## Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** SFS EN 1982 Copper and Copper Alloys - Ingots and Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

Chemical Composition		
Aluminium	Al %	0.010 max.
Iron	Fe %	0.500 max.
Nickel	Ni %	2.000 max.
Phosphorus	P %	0.050 max.
Lead	Pb %	3.000 - 6.000
Sulphur	S %	0.100 max.
Antimony	Sb %	0.300 max.
Silicon	Si %	0.010 max.
Tin	Sn %	2.000 - 3.500
Zinc	Zn %	7.000 - 9.500
Cu + Ni	Cu%+Ni%	81.000 - 86.000
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	180 - 220
Yield Strength in Mpa	85 - 100
Elongation in %	12 - 15
Reduction of Area in %	-
Hardness in HB	60 - 70
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB490K	BS	British	Ingot and Casting
CC490K	UNI	Italy	Ingot and Casting
CuSn3Zn8Pb5-C	UNI	Italy	Ingot and Casting
CC490K	MSZ	Hungary	Ingot and Casting
CuSn3Zn8Pb5-C	MSZ	Hungary	Ingot and Casting
CC490K	AFNOR NF	France	Ingot and Casting
CuSn3Zn8Pb5-C	AFNOR NF	France	Ingot and Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India