

Material: SS 2304

Standard Specification for Stainless Steel - SS Steel 23 04

Group: Ferrous Stainless Steel Alloys

Sub Group: SS 2304 Stainless Steel - SS Steel 23 04

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar, Wire, Shapes and Forging

Chemical Composition		
Carbon	C %	0.260 - 0.350
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	12.000 - 14.000
Nickel	Ni %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	485 min.
Elongation in %	15 min.
Reduction of Area in %	25 min.
Hardness in HB	269 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4028	EN	European Union	Forging
SUS 420J2	JIS	Japan	Forging
30CH13	GOST	Russia	Bar, Wire, Shapes and Forging
420	AISI	USA	Bar, Wire, Shapes and Forging
X 30Cr13	UNI	Italy	Bar, Wire, Shapes and Forging
420 S 45	BS	British	Bar, Wire, Shapes and Forging
A743 CA20	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India