

Material: STAS T15MoCrNi30R

Standard Specification for Cryogenic Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: STAS T15MoCrNi30R Cryogenic Steel Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.200	Normalizing + Tempering or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 - 0.7500		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	1.350 - 1.850		
Nickel	Ni %	2.500 - 3.500		
Molybdenum	Mo %	0.300 - 0.600		
Copper	Cu %	0.300 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-352 Grade LC2-1	ASME	USA	Casting
1.6783	DIN	Germany	Casting
20NCD12M	AFNOR NF	France	Casting
J42215	UNS	USA	Casting
1.6783	EN	European Union	Casting
J42015	UNS	USA	Casting
A352 LC2-1	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com