

# Material: UNE CW611N

## Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

**Group:** Non Ferrous Copper Alloys

**Sub Group:** UNE CW611N Copper and Copper Alloy Rod for Free Machining Purpose

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Rod

Chemical Composition		
Aluminium	Al %	0.050 max.
Iron	Fe %	0.300 max.
Nickel	Ni %	0.300 max.
Lead	Pb %	0.800 - 1.600
Tin	Sn %	0.300 max.
Other	Ot %	0.200 max.
Copper	Cu %	59.000 - 60.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Solution Heat Treated	

Mechanical Properties	
Tensile Strength in Mpa	360 min.
Yield Strength in Mpa	220 - 300
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in HV	80 - 155
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn39Pb1	DIN	Germany	Rod
CuZn39Pb1	BS	British	Rod
CW611N	BS	British	Rod
CuZn39Pb1	UNE	Spain	Rod
CuZn39Pb1	UNI	Italy	Rod
CW611N	UNI	Italy	Rod
CW611N	DIN	Germany	Rod

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India