

Material - UNE EN 1676 AB-44100

Standard Specification for Aluminium and Aluminium Alloys - Alloyed Ingots for Remelting

Group - Non-Ferrous Aluminium Alloy

Sub Group - UNE EN 1676 for Aluminium and Aluminium Alloys - Alloyed Ingots for Remelting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.		
Iron	Fe %	0.550 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.550 max.		
Silicon	Si %	10.000 - 13.500		
Titanium	Ti %	0.150 max.		
Lead	Pb %	0.100 max.		
Zinc	Zn %	0.150 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	-
			Yield Strength in Mpa As-Cast	-
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in HB	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AB-44100	DIN	Germany	Ingot and Casting
EN AB-44100	BS	British	Ingot and Casting
EN AB-44100	SFS	Finland	Ingot and Casting
Al Si12(b)	ISO	International	Casting
EN AB-44100	UNI	Italy	Ingot and Casting
EN AB-44100	CSN	Czech Republic	Ingot and Casting
EN AB-44100	BDS	Bulgaria	Ingot and Casting