

Material: UNE EN ISO 18273 Al 4047A

Standard Specification for Wires and Rods for Welding of Aluminium and Aluminium Alloys

Group: Non-Ferrous Aluminium Alloy

Sub Group: UNE EN ISO 18273 Wires and Rods for Welding of Aluminium and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Wire and Rod

Chemical Composition			Heat Treatment	
Copper	Cu %	0.030 max.	As-Cast	
Iron	Fe %	0.600 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.150 max.		
Silicon	Si %	11.000 - 13.000		
Titanium	Ti %	0.150 max.		
Beryllium	Be %	0.0003 max.		
Zinc	Zn %	0.200 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN Al 4047A	DIN	Germany	Wire and Rod
EN Al 4047A	BS	British	Wire and Rod
EN Al 4047A	SFS	Finland	Wire and Rod
Al Si12(a)	ISO	International	Casting
EN Al 4047A	UNI	Italy	Wire and Rod
EN Al 4047A	CSN	Czech Republic	Wire and Rod
EN Al 4047A	BDS	Bulgaria	Wire and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com