

Material: UNE EN ISO 18273 AlSi7Mg

Standard Specification for Wires and Rods for Welding of Aluminium and Aluminium

Group: Non-Ferrous Aluminium Alloy

Sub Group: UNE EN ISO 18273 Wires and Rods for Welding of Aluminium and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Wire and Rod

Chemical Composition			Heat Treatment													
Copper	Cu %	0.020 max.	As-Cast													
Iron	Fe %	0.200 max.														
Magnesium	Mg %	0.300 - 0.450														
Manganese	Mn %	0.100 max.														
Silicon	Si %	6.500 - 7.500														
Titanium	Ti %	0.200 max.														
Beryllium	Be %	0.0003 max.														
Zinc	Zn %	0.100 max.														
Other	Ot%	0.150 max.	Mechanical Properties <table><tr><td>Tensile Strength in Mpa</td><td>-</td></tr><tr><td>Yield Strength in Mpa</td><td>-</td></tr><tr><td>Elongation in %</td><td>-</td></tr><tr><td>Reduction of Area in %</td><td>-</td></tr><tr><td>Hardness in HB</td><td>-</td></tr><tr><td>Impact in Joule</td><td>-</td></tr></table>		Tensile Strength in Mpa	-	Yield Strength in Mpa	-	Elongation in %	-	Reduction of Area in %	-	Hardness in HB	-	Impact in Joule	-
Tensile Strength in Mpa	-															
Yield Strength in Mpa	-															
Elongation in %	-															
Reduction of Area in %	-															
Hardness in HB	-															
Impact in Joule	-															
Aluminium	Al %	Balance														
-	-	-														
-	-	-														
-	-	-														
-	-	-														
-	-	-														

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AlSi7Mg	DIN	Germany	Wire and Rod
AlSi7Mg	BS	British	Wire and Rod
AlSi7Mg	UNI	Italy	Wire and Rod
AlSi7Mg	ISO	International	Wire and Rod
AlSi7Mg	MSZ	Hungary	Wire and Rod
AlSi7Mg	CSN	Czech Republic	Wire and Rod
AlSi7Mg	BDS	Bulgaria	Wire and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com