

Material: UNE X 2 CrNiMoN 17 13

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: UNE X 2 CrNiMoN 17 13 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar, Wire, Rod and Forging

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	16.500 - 18.500
Molybdenum	Mo %	4.000 - 5.000
Nickel	Ni %	12.500 - 14.500
Nitrogen	N %	0.120 - 0.220
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	580 - 800
Yield Strength in Mpa	270 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in HB	250 max.
Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4439	BS	British	Tube
1.4439	DIN	Germany	Steel
1.4439	EN	European Union	Steel
X2CrNiMoN17 13 5	DIN	Germany	Steel
X2CrNiMoN17 13 5	ISO	International	Steel
X2CrNiMoN17 13 5 KW	ONORM	Australia	Steel
X2CrNiMoN17-13-5	AFNOR NF	France	Steel, Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India