

Material: UNE X 6 CrNiMoNb 17 12 2

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: UNE X 6 CrNiMoNb 17 12 2 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar, Wire, Rod and Forging

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	16.500 - 18.500
Molybdenum	Mo %	2.000 - 2.500
Nickel	Ni %	10.500 - 13.500
Niobium	NB %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	510 - 740
Yield Strength in Mpa	215 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in HB	230 max.
Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4580	EN	European Union	Tube
1.458	DIN	Germany	Steel, Sheet, Plate and Strip
10216-5	BS	British	Steel, Sheet, Plate and Strip
X6CrNiMoNb17 12 2	DIN	Germany	Steel, Sheet, Plate and Strip
X6CrNiMoNb17 12 2 KKW	ONORM	Australia	Steel
X6CrNiMoNb17-12-2	AFNOR NF	France	Steel, Bar and Rods
318 S 17	BS	British	Steel and Wire

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India