

# Material: UNI CW408J

## Standard Specification for Copper-Nickel-Zinc Alloy Rod

**Group:** Non Ferrous Copper Alloys

**Sub Group:** UNI CW408J Copper-Nickel-Zinc Alloy Rod

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Rod

Chemical Composition		
Iron	Fe %	0.300 max.
Manganese	Mn %	0.700 max.
Nickel	Ni %	17.000 - 19.000
Lead	Pb %	0.500 - 1.500
Tin	Sn %	0.200 max.
Other	Ot %	0.200 max.
Copper	Cu %	59.500 - 62.500
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Solution Heat Treated

Mechanical Properties	
Tensile Strength in Mpa	420 min.
Yield Strength in Mpa	260 min.
Elongation in %	3 min.
Reduction of Area in %	-
Hardness in HV	115 - 190
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuNi18Zn19Pb1	DIN	Germany	Rod
CuNi 18 Zn 19 Pb	DIN	Germany	Rod
Ns6218Pb	DIN	Germany	Rod
C 7941 B	JIS	Japan	Rod, Bar and Wire
MZN181	PN	Poland	Rod
NS 113	BS	British	Plate
CuNi18Zn19Pb1	UNI	Italy	Rod

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India