

## Material: UNI EN 1706 AC-45300

### Standard Specification for Aluminium and Aluminium Alloys - Castings

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** UNI EN 1706 Aluminium and Aluminium Alloys - Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment													
Copper	Cu %	1.000 - 1.500	As-Cast													
Iron	Fe %	0.650 max.														
Magnesium	Mg %	0.350 - 0.650														
Manganese	Mn %	0.550 max.														
Nickel	Ni %	0.250 max.														
Silicon	Si %	4.500 - 5.500														
Lead	Pb %	0.150 max.														
Tin	Sn %	0.050 max.														
Titanium	Ti %	0.200 max.														
Zinc	Zn %	0.150 max.														
Other	Ot%	0.150 max.														
Aluminium	Al %	Balance														
-	-	-			<b>Mechanical Properties</b> <table border="1"> <tr> <td>Tensile Strength in Mpa</td> <td>170 - 280</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>120 - 210</td> </tr> <tr> <td>Elongation in %</td> <td>1 - 3</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in HB</td> <td>80 - 110</td> </tr> <tr> <td>Impact in Joule</td> <td>-</td> </tr> </table>		Tensile Strength in Mpa	170 - 280	Yield Strength in Mpa	120 - 210	Elongation in %	1 - 3	Reduction of Area in %	-	Hardness in HB	80 - 110
Tensile Strength in Mpa	170 - 280															
Yield Strength in Mpa	120 - 210															
Elongation in %	1 - 3															
Reduction of Area in %	-															
Hardness in HB	80 - 110															
Impact in Joule	-															
-	-	-														
-	-	-														
-	-	-														

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-45300	DIN	Germany	Casting
EN AC-45300	EN	European Union	Casting
LM16	BS	British	Ingot and Casting
EN AC-45300	SFS	Finland	Casting
EN AC-45300	AFNOR NF	France	Casting
EN AC-45300	CSN	Czech Republic	Casting
EN AC-45300	BDS	Bulgaria	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)