

Material: UNI EN-1753 MC21121

Standard Specification for Magnesium and Magnesium Alloys - Ingots and Castings

Group: Non-Ferrous Magnesium Alloy

Sub Group: UNI EN-1753 Magnesium and Magnesium Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.000 - 10.000	As-Cast or Solution Treated or Fully Treated	
Copper	Cu %	0.200 max.		
Iron	Fe %	0.030 max.		
Nickel	Ni %	0.010 max.		
Other	Ot%	0.050 max.		
Silicon	Si %	0.300 max.		
Zinc	Zn %	0.300 - 1.000		
Magnesium	Mg %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 140 - 235 Yield Strength in Mpa 75 - 110 Elongation in % 1 - 6 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Mg-Al9Zn	ISO	International	Bar and Wire
MgAl9Zn Class3	JIS	Japan	Casting
EN-MC21121	ONORM	Australia	Ingot and Casting
EN-MC21121	DIN	Germany	Ingot and Casting
EN-MC21121	CSN	Czech Republic	Ingot and Casting
EN-MC21121	MSZ	Hungary	Ingot and Casting
EN-MC21121	PN	Poland	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India