

Material: UNI X 12 Cr 9 KG

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: UNI X 12 Cr 9 KG Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Isothermal Annealing	
Silicon	Si %	0.500 - 1.000		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	8.000 - 10.000		
Molybdenum	Mo %	0.900 - 1.100		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	640 - 890
-	-	-	Yield Strength in Mpa	480 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	280 max.
-	-	-	Impact in Joule	30 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7386+I	EN	European Union	Steel and Tube
1.7386+I	DIN	Germany	Steel and Tube
1.7386+I	DIN	Germany	Steel and Tube
X11CrMo91TA	ISO	International	Steel and Tube
X11CrMo91TN+TT	ISO	International	Steel and Tube
X12CrMo9 1	DIN	Germany	Steel and Tube
17116	CSN	Czech Republic	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com