

Material: UNI X 2 CrNiMoCuDIN 25-7-4

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: UNI X 2 CrNiMoCuDIN 25-7-4 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar and Rods

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	3.000 - 4.000
Nickel	Ni %	6.000 - 8.000
Tungsten	W %	0.500 - 1.000
Copper	Cu %	0.500 - 1.000
Nitrogen	N %	0.200 - 0.300
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	730 - 930
Yield Strength in Mpa	530 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HB	290 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4501	BS	British	Tube
1.4501	EN	European Union	Steel, Sheet, Plate and Strip
1.4501	DIN	Germany	Steel, Sheet, Plate and Strip
X2CrNiMoCuDIN25-7-4	AFNOR NF	France	Steel
X2CrNiMoCuDIN25-7-4	DIN	Germany	Steel, Sheet, Strip and Plate
X2CrNiMoCuDIN25-7-4	EN	European Union	Steel and Tube
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India