

Material: UNS A03600

Standard Specification for Aluminium and Aluminium Alloy - Ingot and Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: UNS Aluminium and Aluminium Alloy - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.600 max.	As-Cast	
Iron	Fe %	2.000 max.		
Magnesium	Mg %	0.400 - 0.600		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.500 max.		
Silicon	Si %	9.000 -10.000		
Tin	Sn %	0.150 max.		
Zinc	Zn %	0.500 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	305 min.
			Yield Strength in Mpa	170 min.
			Elongation in %	2.5 min.
			Reduction of Area in %	-
			Hardness in HB	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
360	AA	USA	Casting
B 275 360.0	ASTM	USA	Casting
A 275 SG100B	ASTM	USA	Casting
B 85 360.0	ASTM	USA	Casting
B 85 SG100B	ASTM	USA	Casting
A03600	SAE	USA	Casting
360.0	NBR	Brazil	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com