

Material: UNS J22000

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J22000 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500 - 0.900		
Nickel	Ni %	0.600 - 1.000		
Molybdenum	Mo %	0.900 - 1.200		
Vanadium	V %	0.030 max.		
Tungsten	W %	0.100 max.		
			Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	484 - 655
Iron	Fe %	Balance	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-487 Grade 12A	ASME	USA	Casting
SA-487 Grade 12B	ASME	USA	Casting
SA-217 Grade WC5	ASME	USA	Casting
A487 12B	ASTM	USA	Casting
A217 WC5	ASTM	USA	Casting
A487 12N	ASTM	USA	Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com