

Material: UNS J23055

Standard Specification for Alloy Steel Casting

Group: Ferrous Mild Steel Alloys

Sub Group: UNS J23055 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 - 0.350	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.450 max.		
Chromium	Cr %	0.700 - 0.900		
Nickel	Ni %	1.650 - 2.000		
Molybdenum	Mo %	0.200 - 0.300		
Tungsten	W %	0.100 max.	Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	1030 min.
Iron	Fe %	Balance	Yield Strength in Mpa	793 min.
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AISI 4330	AISI	USA	Forging, Bar, Wire, and Shape
4330	SAE	USA	Bar, Tube, Sheet, Strip and Forging
4340	AMS	USA	Bar and Forging
A732 9Q	ASTM	USA	Casting
J23015	UNS	USA	Casting
A487 10A	ASTM	USA	Casting
SA 487 10A	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com