

Material: UNS J91550

Standard Specification for Alloy Steel Casting

Group: Ferrous Stainless Steel Alloys

Sub Group: UNS J91550 Alloy Steel Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	3.500 - 4.500		
Molybdenum	Mo %	0.400 - 1.000		
Tungsten	W %	0.100 max.		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 760 min. Yield Strength in Mpa 550 min. Elongation in % 15 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A757 Grade E3N	ASTM	USA	Casting
GX 5 CrNiMo 13-4	DIN	Germany	Casting
1.4407	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com