

# Material: UNS J95405

## Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

**Group:** Non-Ferrous Cobalt Alloys

**Sub Group:** UNS J95405 Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

**Application:** Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment
Carbon	C %	0.350 - 0.750	
Silicon	Si %	2.500 max.	
Manganese	Mn %	2.000 max.	
Chromium	Cr %	17.000 - 21.000	
Molybdenum	Mo %	0.500 max.	
Phosphorus	P %	0.040 max.	
Sulphur	S %	0.040 max.	
Nickel	Ni %	37.000 - 41.000	
Iron	Fe %	Balance	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
			As-Cast or Annealing or Age Hardning

  

Mechanical Properties	
Tensile Strength in Mpa	450 min.
Yield Strength in Mpa	-
Elongation in %	4 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
13505 Grade 14	IS	India	Casting
A 297 Grade HU	ASTM	USA	Casting
N08004	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India