

Material: UNS K66979

Standard Specification for Nickel-Iron Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Group: Non-Ferrous Nickel Alloys

Sub Group: UNS K66979 Nickel-Iron Alloy Pipe, Tube, Sheet, Strip, Plate, Round Bar, Flat Bar, Forging Stock, Hexagon and Wire

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.750 max.		
Manganese	Mn %	0.750 max.		
Chromium	Cr %	14.000 - 16.000		
Molybdenum	Mo %	3.000 - 4.500		
Aluminium	Al %	0.750 - 1.300		
Boron	B %	0.008 - 0.016		
Titanium	Ti %	2.700 - 3.300		
Tungsten	W %	3.750 - 4.500		
Nickel	Ni %	42.000 - 48.000		
			Mechanical Properties	
Phosphorus	P %	0.015 max.	Tensile Strength in Mpa	1402.4 min.
Sulphur	S %	0.015 max.	Yield Strength in Mpa	1013.2 min.
Zirconium	Zr %	0.050 max.	Elongation in %	12.8 min.
Iron	Fe %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Udimet D-979	Gravity	India	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
N09979	UNS	USA	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com