

Material: UNS N06626

Standard Specification for Nickel and Nickel-Related Alloys

Group: Non-Ferrous Nickel Alloys

Sub Group: SAE 5879 Nickel and Nickel-Related Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Sheet, Strip and Foil

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.150 max.
Manganese	Mn %	0.500 max.
Chromium	Cr %	20.000 - 23.000
Molybdenum	Mo %	8.000 - 10.000
Iron	Fe %	5.000 max.
Aluminium	Al %	0.400 max.
Cobalt	Co %	1.000 max.
Phosphorus	P %	0.015 max.
Sulphur	S %	0.015 max.
Titanium	Ti %	0.400 max.
Niobium	Nb %	3.150-4.150
Nitrogen	N %	0.020 max.
Nickel	Ni %	Balance
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	827 min.
Yield Strength in Mpa	417 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 625 LCF	Gravity	India	Sheet, Strip and Foil
5879	SAE	USA	Sheet, Strip and Foil
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India