

Material: UNS N07751

Standard Specification for Nickel and Nickel-Related Alloys

Group: Non-Ferrous Nickel Alloys

Sub Group: UNS N07751 Nickel and Nickel-Related Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Round Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 17.000		
Aluminium	Al %	0.900 - 1.500		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Niobium	Nb %	0.700 - 1.200		
Iron	Fe %	5.000 - 9.000		
Titanium	Ti %	2.000 - 2.600	Mechanical Properties	
Nickel	Ni %	Balance	Tensile Strength in Mpa	1100 - 1300
-	-	-	Yield Strength in Mpa	630 - 850
-	-	-	Elongation in %	12 - 33
-	-	-	Reduction of Area in %	20 - 32
-	-	-	Hardness in HRC	32 - 40
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 751	SAE	USA	Round Bar
NiCr 15 Fe 7 TiAl	ISO	International	Round Bar
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com