

Material: UNS S30409

Standard Specification for Casting Austenitic Chromium Nickel Stainless Steel

Group: Ferrous Stainless Steel Alloys

Sub Group: UNS S30409 Casting Austenitic Chromium Nickel Stainless Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: General High Temperature and General Corrosive Service

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.100	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	8.000 - 11.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	525 min.
-	-	-	Yield Strength in Mpa	225 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LH 19 N 14 G	PN	Poland	Casting
J92604	UNS	USA	Casting
19 Cr12 Ni 4 Mn	Common	-	Casting
1.4832	DIN	Germany	Casting
A 297 HG10MnN	ASTM	USA	Casting
A743 HG10MnN	ASTM	USA	Casting
A351 HG10MnN	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com